

**DriscoPlex® 4600 IPS - Iron Pipe Sizes**

IPS		DR 19			DR 17		
ASTM F714 PR		PR = 112 psi			PR = 125 psi		
AWWA C906 PC		PC = 88 psi			PC = 100 psi		
Pipe Size, in.	OD, in.	Min Wall	Avg. ID	Wgt.	Min Wall	Avg. ID	Wgt.
		in.	in.	lbs/ft	in.	in.	lbs/ft
2	2.375	0.125	2.110	0.39	0.265	3.938	1.55
4	4.50	0.237	3.998	1.39	0.265	3.938	1.55
6	6.63	0.349	5.886	3.02	0.390	5.798	3.36
8	8.63	0.454	7.663	5.12	0.507	7.550	5.69
10	10.75	0.566	9.551	7.96	0.632	9.410	8.83
12	12.75	0.671	11.327	11.20	0.750	11.160	12.43

**DriscoPlex® 4700 DIPS - Ductile Iron Pipe**

DIPS		DR 19			DR 17		
ASTM F714 PR		PR = 112 psi			PR = 125 psi		
AWWA C906 PC		PC = 88 psi			PC = 100 psi		
Pipe Size, in.	OD, in.	Min Wall	Avg. ID	Wgt.	Min Wall	Avg. ID	Wgt.
		in.	in.	lbs/ft	in.	in.	lbs/ft
4	4.80	0.253	4.264	1.59	0.282	4.201	1.76
6	6.90	0.363	6.130	3.28	0.406	6.040	3.64
8	9.05	0.476	8.040	5.64	0.532	7.921	6.26
10	11.10	0.584	9.861	8.49	0.653	9.716	9.42
12	13.20	0.695	11.727	12.00	0.776	11.554	13.32

This product flyer is intended for reference purposes. It should not be used in place of the advice from a licensed Professional Engineer. Pressure Ratings and Pressure Class are based on operating temperature up to 80°F. Pressure class is based on a 0.5 Design Factor for water application from AWWA while Pressure Rating is based on a 0.63 Design Factor per PPI TR-41. Average inside diameter is calculated using Nominal OD and Minimum Wall plus 6% for use in estimating fluid flow. Actual ID will vary. When designing components to fit the pipe ID, refer to pipe dimensions and tolerances in the applicable pipe manufacturing specification. Additional information available at [www.performancepipe.com](http://www.performancepipe.com)