

For more information and technical assistance contact:

Chevron Phillips Chemical Company LP
P.O. Box 4910
The Woodlands, TX 77387-4910
800.231.3260



AlphaPlus® C30+HA Sales Specifications

Characteristics	Method	Units	Target	Minimum	Maximum	Note
Less than C ₂₄	GLC	Wt %	--	--	0.10	--
C ₂₄₋₂₈ max.	GLC	Wt %	--	--	8.00	--
C ₃₀₊ min.	GLC	Wt %	--	92.0	--	--
Kinematic Viscosity @ 210°F (99°C)	ASTM D445	cSt	--	--	12.0	--
Color, Unfiltered	SOP PC703.000	Saybolt	---	0	---	---
Appearance	SOP PC714.000	--	--	Pass	--	note 1
API Gravity @ 60°F	ASTM D287	--	--	--	--	note 2
Specific Gravity @ 60°F/60°F	ASTM D287	---	---	---	---	note 2
Dropping Point	ASTM D3954	°F	--	150	--	--

1. Clear and substantially free of visual impurities
2. Run and record

MSDS #10000006617

Revision Date September 2022



Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the user's specific application. Chevron Phillips Chemical Company LP does not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, express or implied, or allegedly arising from any usage of any trade or from any course of dealing in connection with the use of the information contained herein or the product itself. The user expressly assumes all risk and liability, whether based in contract, tort or otherwise, in connection with the use of the information contained herein or the product itself. Further, information contained herein is given without reference to any intellectual property issues, as well as federal, state or local laws which may be encountered in the use thereof. Such questions should be investigated by the user.